

TEST REPORT

COMPANY NAME:

ADDRESS

EMAIL:

ATTN:

TEL:

FAX:

MECDEX

LIBERMANN International
P.O Box-1166 Harrar, Wazirabad
Road, Sialkot-51310, Pakistan

ali.anwar@libermann.com

Ali Anwar

+92 52 3252201-up to 5

+92 52 3252208

Report No.:

TRF No.:

Date In:

Date Out:

No. Of Working Days:

Pretest for Buyer

Temperature & Humidity:

FTL-1346/020923

FTL-1346/020923

01-09-2023

04-09-2023

04 Days

Not Listed

23°C ± 2 53 ± 5%

Sample Description:	Armor Tech Gloves
Color(s):	Black
Lab Id Color(S):	Black
P.O. No(s):	Not Listed
Article No(s):	OD-815
Season:	Not Listed
Quantity Submitted:	10 Pairs
Country of Origin:	Pakistan
Country of Destination:	Europe
Dept:	Not Listed
End Use:	Not Listed

Submitted Fiber Content:	Not Listed
Multi Layers	Goatskin Leather
Test Requested:	EN 388:2016+A1:2018, EN ISO 21420:2020
Submitted Care Instruction:	Not Listed
Suggested Care Instruction:	Not Listed

PHOTO OF THE SUBMITTED SAMPLE



EN 388:2016+A1 2018



3 1 3 1 X P

FIRST TESTING LAB
AUTHORIZED SIGNATORIES


Test Conducted by


Test Checked by


Approved By

SUMMARY OF TEST RESULTS

TEST PROPERTY	Standard Method	Results	Comments
ABRASION RESISTANCE	EN 388:2016+A1:2018	Level-3	
BLADE CUT RESISTANCE	EN 388:2016+A1:2018	Level-1	
TEAR RESISTANCE	EN 388:2016+A1:2018	Level-3	
PUNCTURE RESISTANCE	EN 388:2016+A1:2018	Level-1	
SIZING	EN ISO 21420:20020	Pass	
DEXTERITY	EN ISO 21420:20020	Level 2	
Impact Resistance	EN 388:2016+A1: 2018	Pass	

Test Results:

Parameter	Test Requirement EN 388:2016+A1:2018			Test Results	Remarks												
6.1 Abrasion Resistance (Cycles) Tested – Palm Portion Used abradant: Klingspor PL 31 B	<table><tr><th>Level of Performance</th><th>Number of Cycles</th></tr><tr><td>1</td><td>100</td></tr><tr><td>2</td><td>500</td></tr><tr><td>3</td><td>2000</td></tr><tr><td>4</td><td>8000</td></tr></table>			Level of Performance	Number of Cycles	1	100	2	500	3	2000	4	8000	>2000 & <8000 Cycles	Complies with Level - 3		
Level of Performance	Number of Cycles																
1	100																
2	500																
3	2000																
4	8000																
6.2 Blade Cut Resistance (<i>i</i>) Tested – Palm <i>Blade Thickness – 0.3 mm</i> <i>Angle of Blade – 24°</i>	<table><tr><th>Level of Performance</th><th>Index (<i>i</i>)</th></tr><tr><td>1</td><td>> 1.2</td></tr><tr><td>2</td><td>≥ 2.5</td></tr><tr><td>3</td><td>≥ 5.0</td></tr><tr><td>4</td><td>≥ 10.0</td></tr><tr><td>5</td><td>≥ 20.0</td></tr></table>			Level of Performance	Index (<i>i</i>)	1	> 1.2	2	≥ 2.5	3	≥ 5.0	4	≥ 10.0	5	≥ 20.0	>1.2& <2.5	Level-1
Level of Performance	Index (<i>i</i>)																
1	> 1.2																
2	≥ 2.5																
3	≥ 5.0																
4	≥ 10.0																
5	≥ 20.0																
6.4 Tear Resistance (Newton) Tested – All Layers	<table><tr><th>Level of Performance</th><th>Strength (N)</th></tr><tr><td>1</td><td>10</td></tr><tr><td>2</td><td>25</td></tr><tr><td>3</td><td>50</td></tr><tr><td>4</td><td>75</td></tr></table>			Level of Performance	Strength (N)	1	10	2	25	3	50	4	75	> 50 & < 75 Newton	Level-3		
Level of Performance	Strength (N)																
1	10																
2	25																
3	50																
4	75																
6.5 Puncture Resistance (Newton) Tested – Palm All Layers Together	<table><tr><th>Level of Performance</th><th>Strength (N)</th></tr><tr><td>1</td><td>20</td></tr><tr><td>2</td><td>60</td></tr><tr><td>3</td><td>100</td></tr><tr><td>4</td><td>150</td></tr></table>			Level of Performance	Strength (N)	1	20	2	60	3	100	4	150	>20 & <60 Newton	Level-1		
Level of Performance	Strength (N)																
1	20																
2	60																
3	100																
4	150																
6.6 Impact Resistance (Load in Kilo Newton) Tested – Palm All Layers Together	<table><tr><th>Level of Performance</th><th>Level-1</th><th>Level-2</th></tr><tr><td>Single Result</td><td>≤ 9.0 KN</td><td>≤ 5.0 KN</td></tr><tr><td>Mean Transmitted Force</td><td>< 7.0 KN</td><td>< 4.0 KN</td></tr></table>			Level of Performance	Level-1	Level-2	Single Result	≤ 9.0 KN	≤ 5.0 KN	Mean Transmitted Force	< 7.0 KN	< 4.0 KN	>7.0	Pass			
Level of Performance	Level-1	Level-2															
Single Result	≤ 9.0 KN	≤ 5.0 KN															
Mean Transmitted Force	< 7.0 KN	< 4.0 KN															

Parameter	Test Requirement EN ISO 21420:2020		Test Results	Remarks												
5.1 Sizing	Size		Lab Analysis	PASS												
	Submitted Size: Small, Medium, Large, X-Large, XX-Large, XXX-Large		➤ Hand Length: All gloves meet the requirements of standard method. ➤ Circumference: All gloves meet the requirements of standard method.													
5.2 Dexterity Pin sizes in millimeters (mm)	<table><tr><th>Level of Performance</th><th>Diameter of Pins (mm)</th></tr><tr><td>1</td><td>11</td></tr><tr><td>2</td><td>9.5</td></tr><tr><td>3</td><td>8</td></tr><tr><td>4</td><td>6.5</td></tr><tr><td>5</td><td>5</td></tr></table>		Level of Performance	Diameter of Pins (mm)	1	11	2	9.5	3	8	4	6.5	5	5	Level-2	Pass
Level of Performance	Diameter of Pins (mm)															
1	11															
2	9.5															
3	8															
4	6.5															
5	5															

The above-specified results are valid for only this glove model.

“End of Report”